

# SOLID 17

Made in Germany

## TECHNICAL DATA

standard:	works standard
lay direction:	ordinary lay
surface:	stainless, galvanized
fill factor:	0,7700
spinning factor:	0,8997



Ø mm	rope weight kg/m	1570 MPa MBL kN	1770 MPa MBL kN
1	0,01	0,8	0,9
2	0,02	3	4
3	0,05	8	9
4	0,09	13	15
5	0,13	21	24
6	0,18	31	35
7	0,25	42	48
8	0,33	55	63
9	0,41	70	79
10	0,51	87	98
11	0,61	103	116
12	0,73	121	140
13	0,85	140	163
14	0,98	168	189
15	1,14	194	219
16	1,31	222	251